

CZE-1200

- **Out line: CZE-1200 is glass fiber and mineral filled electric conductive grade and has stably low electric resistibility.**
- **Color: Black**

Engineering Properties of CZE-1200

Properties	Test Method	Unit	CZE-1200
General Information			GF & Others Conductive
<ASTM>			
Physical			
Specific gravity	D-792	-	1.90
Water absorption, 23deg. /24Hrs. /in water	D-570	Wt. %	0.03
Mold shrinkage, MD /TD ^a	D-955	%	0.20/0.90
Mechanical			
Tensile strength	D-638	MPa	100
Tensile modulus	D-638	MPa	20000
Tensile elongation at break	D-638	%	0.6
Poisson's ratio	-	-	0.34
Flexural strength	D-790	MPa	150
Flexural modulus	D-790	MPa	19000
Flexural elongation at break	D-790	%	0.8
Izod impact strength	D-256	J/m	
notched / un notched			60/200
Compressive strength	D-695	MPa	120
Rockwell hardness, R/M	D-785	-	121/100
Coefficient of friction ^b , static /dynamic	-	-	0.32/0.32
Thermal			
Distortion temp. of under load, 1.82MPa	D-648	°C	265
Coefficient of thermal expansion ^c , -30 to 90°C	D-696	m/mK	2.0x10 ⁻⁵
UL Flammability ^d , t~0.8mm	UL-94	-	V-0
Electrical			
Dielectric strength, t=1.6mm	D-149	kv/mm	-
Dielectric constant, 1MHz	D-150	-	-
Dissipation factor, 1MHz	D-150	-	-
Comparative tracking index (CTI)	D-3638	Volt	-
Arc resistance	D-495	sec.	-
Volume resistibility	D-257	Ohm.cm	10 ²⁻³
Process Conditions			
Cylinder temperature	-	°C	300-340
Mold temperature	-	°C	120-150

a: MD; Mold direction, TD; Transverse direction, b: P=150KPa, V=0.3m/s, PPS vs. carbon steel,
c: Average value of MD & TD, d: UL file No. E53829



★Please refer to Material Safety Data Sheet for safety precautions prior to use. The information contained in this data sheet is based on tests or research DIC Corporation ("DIC") believes to be reliable, but no warranty is given by DIC concerning the accuracy or completeness thereof. The supply of the information does not release the recipient from the obligation to test the products as to their suitability for the intended applications and processes. DIC has no liability for any consequence of the application, processing or use of the information or the products. Information concerning the application of the products is not and should not be construed as a warranty as to non-infringement of intellectual property for a particular application.