

Out-Gas from Melting Resin

Main outgas components of PPS at the injection process are H₂O and CO₂, and additional gas is coming out. The following table is organic gas captured at the following condition;

Testing material: FZ-1140 and FZ-2140 pellets

Melting condition: 15 min. at 320C

The captured gas from FZ-1140 that is cured polymer based compound contains mainly high boiling point components (Boiling Point; over 280C, segment No. 7-15). On the other hand, the captured gas from FZ-2140 which is linear polymer based compound contains mainly low boiling point components such as Xylene. Most of them are coming from PPS polymer.

Table Out-gas from melted PPS resin (320C/15min.)

No.	Gas components	Chemical name	Boiling point °C	FZ- 1140	FZ- 2140
1		Xylene	139-145	2.1	24.1
2		Phenol	182	2.6	2.6
3	NMP	N-methyl-2-pyrrolidone	202	1.0	0.4
4		chloro aniline	232	1.9	-
5		methyl chloro aniline	>230	1.6	-
6			>230	3.6	0.4
7			>280	15.3	2.2
8			>280	2.5	-
9			>280	35.5	3.6
10			>280	11.9	5.4
11			>280	1.1	-
12			>280	1.1	-
13			>280	2.9	3.0
14			>280	3.7	2.2
15			>280	13.2	1.9

※Above value is correlation data based on FZ1140 data as 100%.



★Please refer to Material Safety Data Sheet for safety precautions prior to use. The information contained in this data sheet is based on tests or research DIC Corporation ('DIC') believes to be reliable, but no warranty is given by DIC concerning the accuracy or completeness thereof. The supply of the information does not release the recipient from the obligation to test the products as to their suitability for the intended applications and processes. DIC has no liability for any consequence of the application, processing or use of the information or the products. Information concerning the application of the products is not and should not be construed as a warranty as to non-infringement of intellectual property for a particular application.