

FZ-6600-R1

- **Outline:** FZ-6600-R1 is a GF/Mineral filled PPS compound which provides excellent weld strength and toughness.
- **Color:** Black

Properties of FZ-6600-R1

Properties	Test Method	Unit	FZ-6600-R1
General Information			GF/Mineral High weld strength
Physical			
Specific gravity	ISO 1183A	-	1.95
Water absorption, 23deg. /24Hrs. /in water	ISO 62	Wt.%	0.02
Mold shrinkage, MD /TD ^a	ISO 294-4	%	0.3 / 0.6
Mechanical			
Tensile strength	ISO 527	MPa	165
Tensile modulus	ISO 527	GPa	21.0
Tensile elongation at break	ISO 527	%	1.0
Poisson's ratio	-	-	-
Flexural strength	ISO 178	MPa	250
Flexural modulus	ISO 178	GPa	20.0
Flexural elongation at break	ISO 178	%	1.4
Charpy impact strength notched / Un notched (23°C)	ISO 179/1eU	kJ/m ²	8 / 30
Compressive strength	ISO 604	MPa	-
Rockwell hardness, R/M	ISO 2039-2	-	121/100
Coefficient of friction ^b , static /dynamic	-	-	-
Thermal			
Distortion temp. of under load, 1.82 / 0.45 MPa	ISO 75-1, -2A	°C	265
Coefficient of thermal expansion ^c , -30 to 90°C	ISO 11359-1, -2	m/mK	1.75x10 ⁻⁵
UL Flammability, t~0.8mm	UL-94	-	V-0
Electrical			
Dielectric strength, t=1.6mm	IEC 60243-1	kv/mm	16
Dielectric constant, 1MHz	IEC 60250	-	5
Dissipation factor, 1MHz	IEC 60250	-	0.006
Comparative tracking index (CTI)	IEC 112	Volt	250
Arc resistance	ASTM D-495	sec.	180
Volume resistivity	IEC 60093	Ohm.cm	10 ¹⁶
Process Conditions			
Cylinder temperature	-	°C	300-340
Mold temperature	-	°C	120-150

a: MD; Mold direction, TD; Transverse direction, b: P=150KPa, V=0.3m/s, PPS vs. carbon steel,
c: Average value of MD & TD,



★Please refer to Material Safety Data Sheet for safety precautions prior to use. The information contained in this data sheet is based on tests or research DIC Corporation ('DIC') believes to be reliable, but no warranty is given by DIC concerning the accuracy or completeness thereof. The supply of the information does not release the recipient from the obligation to test the products as to their suitability for the intended applications and processes. DIC has no liability for any consequence of the application, processing or use of the information or the products. Information concerning the application of the products is not and should not be construed as a warranty as to non-infringement of intellectual property for a particular application.