

SE-760

- **Out line: SE-760 is a glass fiber and mineral filled PPS/PPE alloy compound that provides low flash and low warp.**
- **Color: Black**

Engineering Properties of SE-760

Properties	Test Method	Unit	SE-760
General Information		<ASTM>	GF & Filler PPS/PPE Alloy
Physical			
Specific gravity	D-792	-	1.82
Water absorption, 23deg. /24Hrs. /in water	D-570	Wt. %	0.02
Mold shrinkage, MD /TD ^a	D-955	%	0.25/0.9
Mechanical			
Tensile strength	D-638	MPa	125
Tensile modulus	D-638	MPa	17000
Tensile elongation at break	D-638	%	0.8
Poisson's ratio	-	-	0.35
Flexural strength	D-790	MPa	200
Flexural modulus	D-790	MPa	16000
Flexural elongation at break	D-790	%	1.4
Izod impact strength notched / un notched	D-256	J/m	75/210
Compressive strength	D-695	MPa	150
Rockwell hardness, R/M	D-785	-	121/100
Coefficient of friction ^b , static /dynamic	-	-	0.36/0.35
Thermal			
Distortion temp. of under load, 1.82MPa	D-648	°C	265
Coefficient of thermal expansion ^c , -30 to 90°C	D-696	m/mK	1.8x10 ⁻⁵
UL Flammability ^d , t~0.8mm	UL-94	-	V-0
Electrical			
Dielectric strength, t=1.6mm	D-149	kv/mm	16
Dielectric constant, 1MHz	D-150	-	5
Dissipation factor, 1MHz	D-150	-	0.007
Comparative tracking index (CTI)	D-3638	Volt	-
Arc resistance	D-495	sec.	160
Volume resistibility	D-257	Ohm.cm	10 ¹⁶
Process Conditions			
Cylinder temperature	-	°C	300-340
Mold temperature	-	°C	120-150

a: MD; Mold direction, TD; Transverse direction, b: P=150KPa, V=0.3m/s, PPS vs. carbon steel,
c: Average value of MD & TD, d: UL file No. E53829



★Please refer to Material Safety Data Sheet for safety precautions prior to use. The information contained in this data sheet is based on tests or research DIC Corporation ("DIC") believes to be reliable, but no warranty is given by DIC concerning the accuracy or completeness thereof. The supply of the information does not release the recipient from the obligation to test the products as to their suitability for the intended applications and processes. DIC has no liability for any consequence of the application, processing or use of the information or the products. Information concerning the application of the products is not and should not be construed as a warranty as to non-infringement of intellectual property for a particular application.