

AMORVON® W-30

- **Out line:** W-30 is a 30% glass fiber reinforced modified PPS compound that is low warp and low warp and is developed to provide for precision moldings.
- **Color:** Black

Engineering Properties of W-30

Properties	Test Method	Unit	W-30
General Information			GF30% Modified PPS "AMORVON"
<ASTM>			
Physical			
Specific gravity	D-792	-	1.57
Water absorption, 23deg. /24Hrs. /in water	D-570	Wt. %	0.06
Mold shrinkage, MD /TD ^a	D-955	%	0.25/1.0
Mechanical			
Tensile strength	D-638	MPa	160
Tensile modulus	D-638	MPa	11000
Tensile elongation at break	D-638	%	1.7
Poisson's ratio	-	-	0.37
Flexural strength	D-790	MPa	220
Flexural modulus	D-790	MPa	10000
Flexural elongation at break	D-790	%	2.2
Izod impact strength notched / un notched	D-256	J/m	65/480
Compressive strength	D-695	MPa	180
Rockwell hardness, R/M	D-785	-	121/100
Coefficient of friction ^b , static /dynamic	-	-	0.35/0.35
Thermal			
Distortion temp. of under load, 1.82MPa	D-648	°C	230
Coefficient of thermal expansion ^c , -30 to 90°C	D-696	m/mK	2.3x10 ⁻⁵
UL Flammability ^d , t~0.8mm	UL-94	-	V-0
Electrical			
Dielectric strength, t=1.6mm	D-149	kv/mm	16
Dielectric constant, 1MHz	D-150	-	4
Dissipation factor, 1MHz	D-150	-	0.002
Comparative tracking index (CTI)	D-3638	Volt	-
Arc resistance	D-495	sec.	120
Volume resistibility	D-257	Ohm.cm	10 ¹⁶
Process Conditions			
Cylinder temperature	-	°C	300-340
Mold temperature	-	°C	120-150

a: MD; Mold direction, TD; Transverse direction, b: P=150KPa, V=0.3m/s, PPS vs. carbon steel,
c: Average value of MD & TD, d: UL file No. E53829



★Please refer to Material Safety Data Sheet for safety precautions prior to use. The information contained in this data sheet is based on tests or research DIC Corporation ("DIC") believes to be reliable, but no warranty is given by DIC concerning the accuracy or completeness thereof. The supply of the information does not release the recipient from the obligation to test the products as to their suitability for the intended applications and processes. DIC has no liability for any consequence of the application, processing or use of the information or the products. Information concerning the application of the products is not and should not be construed as a warranty as to non-infringement of intellectual property for a particular application.